

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2002-105249

(43)Date of publication of application : 10.04.2002

(51)Int.Cl. C08L 21/00
B60C 1/00
B60C 15/06
C08K 5/3477
// (C08L 21/00
C08L 61:04)

(21)Application number : 2001-229750

(71)Applicant : BRIDGESTONE CORP

(22)Date of filing : 30.07.2001

(72)Inventor : FUKUHARA NOBUHIKO
NISHIZAKI TOMOYASU

(30)Priority

Priority number : 2000228865 Priority date : 28.07.2000 Priority country : JP

(54) RUBBER COMPOSITION FOR BEAD FILLER

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a rubber composition for a bead filler having a high modulus without reduction of breaking strength compared with a conventional bead filler.

SOLUTION: The rubber composition for the bead filler and a pneumatic tire consisting of 100 pts.wt. of a rubber component, 5-40 pts.wt. of a phenolic thermosetting resin, 4-20 pts.wt. of hexamethylenetetramine to 100 pts.wt. of the phenolic thermosetting resin, and 10-80 pts.wt. of melamine derivatives relative to 100 pts.wt. of the phenolic thermosetting resin.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office